

PRODUCT DATA SHEET

CAP527 LOW SHEEN TOP COAT

PRODUCT	CAP527 low sheen acrylic top coat
DESCRIPTION/USES	CAP527 is a low VOC, water based coating for use over CAP508 in wet, humid and damp areas, or to achieve Group 1 to AS3837 on wood substrates.
SURFACE PREPARATION	All surfaces should be clean, dry, and free of dust, grease or other contaminants.

APPLICATION INFORMATION

MATERIAL PREPARATION	Mix thoroughly before application
METHOD	Airless spray, brush or roller.
DRYING TIME	Dry to Touch: 1/2 hour at 24°C and 50% relative humidity (RH) Re-Coat: 2 to 4 hours at 24°C and 50% relative humidity (RH) Full Cure: 20 days
THINNING	Do NOT thin
CLEAN UP	Water
HMIS	Health: 1, Flammability: 0, Reactivity: 0, Personal Protection: E.
ENVIRONMENTAL	Consult with local regulatory and governmental agencies for methods of disposal.

SPECIFICATIONS

COLOUR	White, can be tinted.
SOLIDS BY VOLUME	43%
WEIGHT PER LITRE	1.12 kg
GLOSS	Low sheen
COVERAGE	10m ² /litre on smooth sealed surfaces per coat
SHELF LIFE	One year
MAXIMUM VOCs	60 grams/litre
CAUTION	Protect from freezing. Do not apply when temperature of paint or surface is below 18°C or above 25°C or relative humidity is above 75%.